









Polyfilm Polyplex Polyester Films

Type: CF122 high clarity PET film 36my

Polyfilm high clarity CF grade Polyester film is designed as base film for technical and industrial applications. Both sides are chemically treated for improved slip and handelability. Treated surface is suitable for adhesion to solvent based inks and coatings. The film is also used in packaging particularly for window application.

Composition



-  chemical treatment
-  standard surface
-  core
-  standard surface
-  chemical treatment

treatment

CF122 = both side chemically treated film

Typical Properties

Provisional data

Property	Units	Nominal	Method	Conditions
Mechanical Properties				
Nominal thickness	μ	36	Polypex Method	
Yield	m ² /kg	19.84	Polypex Method	
Unit weight	g/m ²	50.4		
Density	g/cm ³	1.4		
Elongation at break	MD %	140	ASTM D-882	

Property	Units		Nominal	Method	Conditions
	TD	%	130		
Tensile strength	MD	kg/cm ²	2000	ASTM D-882	
	TD	kg/cm ²	2100		
Thermal Properties					
Heat shrinkage	MD	%	1.6	ASTM D-1204	150 Deg. C/30 minutes
	TD	%	0.2		
Surface Properties					
Co-efficient of friction static			0.45	ASTM D-1894	
Co-efficient of friction dynamic			0.35	ASTM D-1894	
Optical Properties					
Haze		%	0.60	ASTM D-1003	

Standard Roll Presentation

Thickness	Core	Length	outside diameter
μ	mm	m	mm
36	76	3000	379
36	152	4500	479
36	152	6000	546

Disclaimer

The information given above is to the best of our knowledge and experience at the time of printing. We make no warranty, express or implied, for specific product properties or as to the fitness of the product for any specific use or purpose. The above data is purely for reader's consideration, investigation and verification and should be read in conjunction with the general conditions for sale.

Edition: 7/2009